



HIGH-PERFORMANCE COATINGS AND LININGS

Short-Form System Reference Guide — Resinous Flooring

READER'S NOTE

Use this guide to quickly select an interior resinous flooring system by facility area, floor use, and service condition. It is a selection reference for architects, engineers, facilities/asset managers, and project teams; it is not a bid-ready specification.

For bid or construction documents, use the companion CSI 3-part specification, Section 09 67 23 - Resinous Flooring, or contact ACC for project-specific guidance.

Prepared as a service by: Atlantic Coating Consultants | Wally Bates | atlantic@tnemec.com | 484-644-5303

OVERVIEW

1. Purpose

This guide summarizes commonly used resinous flooring systems for interior concrete floors and exterior/elevated pedestrian decks: 100% solids epoxy systems, water-based epoxy systems, urethane cement systems, and a reinforced waterproof deck coating. Systems are organized by resin family and duty level so they can be used across institutional, municipal, commercial, industrial, water and wastewater facilities.

2. How to Use This Guide

- Start with the Quick Locator Index if you know the facility area or floor use. Click the applicable system to jump to its schedule.
- If you know the service condition, go directly to the system table and match the Condition and Typical Locations. Light Duty = foot traffic and light carts; Moderate Duty = heavy foot traffic, rolling loads, frequent cleaning; Heavy Duty = thermal shock, impact, hot-water washdown, chemical exposure.
- Use Surface Preparation, Coat Schedule, and Total Build for budgeting, work-order planning, and contractor pricing. Flooring coats are applied at coverage rate (SF/gal or SF/kit); Total Build is the nominal system thickness.
- Contact ACC to confirm project-specific exposure, slab moisture-vapor condition, existing coating condition, color/aggregate selection, slip resistance, or full CSI specification requirements.

3. Basis of Design

Products scheduled herein are manufactured by Tnemec Company, Inc., 123 West 23rd Ave, North Kansas City, MO 64116, (816) 483-3400, www.tnemec.com, and are listed as the basis of design for the performance, appearance, and warranty characteristics described. Substitution requirements are set out in Article 2.1 of Section 09 67 23.

4. Not Covered in This Guide

Typical Locations are intentionally broad so the guide can be used across building and facility types. Wall, ceiling and structural coatings are maintained in the companion Architectural Interior & Exterior reference; process-facility systems are maintained in the ACC Water Treatment and Wastewater Treatment references. Vehicular traffic deck coatings, secondary containment linings and immersion-service floors are not covered here; contact ACC.

5. General Application & Warranty Notes

- Follow the current manufacturer product data sheet for substrate, ambient, dew-point, humidity, ventilation, surface-profile, and application requirements.
- Test concrete for moisture vapor emission (ASTM F1869) and relative humidity (ASTM F2170) before installation. Where results exceed the limits on the product data sheet, use a moisture-vapor-tolerant primer



or base coat (Series 208 Epoxoprime MVT, Series N241 Ultra-Tread MVT or Series N242 Ultra-Tread S) as noted in the schedule, or contact ACC.

- Concrete surface-profile requirements vary by system; confirm the specified ICRI CSP and verify surface preparation before full-scale work. New concrete shall be cured a minimum of 28 days unless the product data sheet permits otherwise.
- Decorative quartz and flake systems: confirm color, blend, and finish texture with a field mock-up before full-scale application. **Perform a mock-up to confirm an acceptable level of slip resistance and any anti-slip additive with the Owner/Architect.**
- Cove base, integral coving, terminations at drains and joints, and treatment of moving cracks are project-specific; detail them on the drawings or confirm with ACC.
- Warranty terms vary by system and project; contact ACC or the manufacturer to confirm applicable coverage.

QUICK LOCATOR INDEX

Find a system by where it goes. Click a system to jump to its full schedule entry. Confirm project-specific conditions before final selection.

Facility Area / Floor Use	Applicable System — Click to Jump
INTERIOR RESINOUS FLOORING SYSTEMS	
Offices, Classrooms & Administrative Areas <i>Dry, light foot traffic.</i>	100% Solids Epoxy — 1/16" Solid Color Epoxy Broadcast — Light Duty Water-Based Epoxy — 1/16" Solid Color Epoxy Broadcast — Light Duty 100% Solids Epoxy — Thin Film Solid Color Water-Based Epoxy — Thin Film Solid Color
Lobbies, Corridors, Reception & Public Spaces <i>Moderate traffic; appearance matters.</i>	100% Solids Epoxy — 1/8" Decorative Quartz Epoxy Broadcast — Moderate Duty 100% Solids Epoxy — 1/16" Decorative Flake Epoxy Broadcast — Light/Moderate Duty 100% Solids Epoxy — 1/8" Solid Color Epoxy Broadcast — Moderate Duty Water-Based Epoxy — 1/8" Decorative Quartz Epoxy Broadcast — Moderate Duty Water-Based Epoxy — 1/16" Decorative Flake Epoxy Broadcast — Light/Moderate Duty Water-Based Epoxy — 1/8" Solid Color Epoxy Broadcast — Moderate Duty
Restrooms, Locker Rooms, Showers & Wet Areas <i>Standing water, frequent cleaning.</i>	Urethane Cement — 1/4" Decorative Quartz Urethane Cement — Heavy Duty Urethane Cement — 1/8" Decorative Quartz Urethane Cement — Moderate/Heavy Duty 100% Solids Epoxy — 1/16" Decorative Flake Epoxy Broadcast — Light/Moderate Duty Water-Based Epoxy — 1/16" Decorative Flake Epoxy Broadcast — Light/Moderate Duty <i>Decorative flake systems are for dry locker and restroom areas; use urethane cement in showers and wet areas.</i>
Kitchens, Food Service, Laundry & Washdown Areas <i>Hot water, thermal shock, grease, heavy cleaning.</i>	Urethane Cement — 1/4" Solid Color Urethane Cement — Heavy Duty Urethane Cement — 1/4" Decorative Quartz Urethane Cement — Heavy Duty

Facility Area / Floor Use	Applicable System — Click to Jump
Mechanical, Electrical, Utility & Pump Rooms	100% Solids Epoxy — 1/8" Solid Color Epoxy Broadcast — Moderate Duty Urethane Cement — 1/4" Solid Color Urethane Cement — Heavy Duty 100% Solids Epoxy — Clear Sealer Water-Based Epoxy — Clear Sealer <i>Use urethane cement where equipment is washed down or rolling loads are heavy; a clear sealer where a dust-proof floor is all that is required.</i>
Laboratories, Chemical Feed & Chemical Storage Rooms <i>Non-immersion chemical splash and spill.</i>	Urethane Cement — 1/4" Solid Color Urethane Cement — Heavy Duty Urethane Cement — 1/4" Decorative Quartz Urethane Cement — Heavy Duty 100% Solids Epoxy — 1/8" Solid Color Epoxy Broadcast — Moderate Duty <i>Secondary containment linings are in the companion Water Treatment and Wastewater Treatment guides.</i>
Workshops, Warehouses, Storage, Loading & Receiving <i>Rolling loads, impact, dry storage.</i>	100% Solids Epoxy — 1/8" Solid Color Epoxy Broadcast — Moderate Duty Urethane Cement — 1/4" Solid Color Urethane Cement — Heavy Duty 100% Solids Epoxy — Clear Sealer Water-Based Epoxy — Clear Sealer
Ground-Floor & Below-Grade Slabs with Moisture-Vapor Concerns <i>Elevated MVT or slab relative humidity.</i>	Urethane Cement — 1/8" Solid Color Urethane Cement — Moderate/Heavy Duty Urethane Cement — 1/8" Decorative Quartz Urethane Cement — Moderate/Heavy Duty Urethane Cement — 1/8" Decorative Flake Urethane Cement — Moderate/Heavy Duty <i>Series 208 Epoxoprime MVT may be used as the primer for the 100% solids epoxy systems on slabs with elevated moisture vapor; see the system notes.</i>
Occupied Buildings / Low-Odor Requirement <i>Phased renovations, limited ventilation.</i>	Water-Based Epoxy — Clear Sealer Water-Based Epoxy — Thin Film Solid Color Water-Based Epoxy — 1/16" Solid Color Epoxy Broadcast — Light Duty Water-Based Epoxy — 1/8" Solid Color Epoxy Broadcast — Moderate Duty Water-Based Epoxy — 1/8" Decorative Quartz Epoxy Broadcast — Moderate Duty Water-Based Epoxy — 1/16" Decorative Flake Epoxy Broadcast — Light/Moderate Duty



RESINOUS FLOORING SYSTEMS

Includes 100% solids epoxy systems (E1), water-based epoxy systems (WB1), urethane cement systems (UC1) and the reinforced waterproof deck coating (WP1). Coats are listed in application order with standard coverage rates; where the system has a note, it follows the coat schedule in italics.

Condition	Typical Locations	Surface Preparation	Coat Schedule (Product — Coverage)	Total Build
E1 — 100% SOLIDS EPOXY SYSTEMS				
Clear Sealer E1.1 <i>Interior Floor • 100% Solids Epoxy finish</i>	Dry storage rooms, mechanical/electrical rooms, warehouses, workshops, back-of-house corridors and general concrete floors where a sealed, dust-proof surface is required without a pigmented finish	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 3 minimum	Primer: Series N222 Deco-Tread (clear) — 160–200 SF/gal Finish: Series N222 Deco-Tread (clear) — 160–200 SF/gal Note: Use Series 248 Everthane as a finish coat for added wear resistance Note: Series 208 can be used as a primer for elevated MVT in the concrete	Applied at coverage rate — see coat schedule
Thin Film Solid Color E1.2 <i>Interior Floor • 100% Solids Epoxy finish</i>	Storage rooms, mechanical/electrical rooms, utility areas, light-traffic corridors, workshops and service areas requiring a pigmented, cleanable floor without broadcast texture	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 3 minimum	Primer: Series 201 Epoxoprime (clear) — 250–320 SF/gal Intermediate: Series N222 Deco-Tread (pigmented) — 160–200 SF/gal Finish: Series N222 Deco-Tread (pigmented) — 160–200 SF/gal Note: Use Series 248 Everthane as a finish coat for added wear resistance Note: Series 208 can be used as a primer for elevated MVT in the concrete	Applied at coverage rate — see coat schedule
1/16" Solid Color Epoxy Broadcast — Light Duty E1.3 <i>Interior Floor • Light Duty • Urethane finish</i>	Offices, conference rooms, administrative areas, private rooms, low-traffic corridors, waiting areas, break rooms, multipurpose rooms and dry storage areas	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 3 minimum	Cove Base (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Primer: Series N222 Deco-Tread — 250–320 SF/gal Broadcast Coat: Series N222 Deco-Tread with 30/50 silica sand — 80–100 SF/gal Grout Coat: Series N222 Deco-Tread (pigmented) — 160–200 SF/gal Finish Coat: Series 248 Everthane with 821 Field Colorant — 500–600 SF/gal	Nominal 1/16" system



Condition	Typical Locations	Surface Preparation	Coat Schedule (Product — Coverage)	Total Build
1/8" Solid Color Epoxy Broadcast — Moderate Duty E1.4 <i>Interior Floor • Moderate Duty • Urethane finish</i>	High-traffic corridors, common areas, assembly/support spaces, break and dining areas, equipment rooms, storage rooms, service areas and other moderate-duty interior floors	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 3 minimum	Cove Base (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Primer: Series N222 Deco-Tread — 250–320 SF/gal First Broadcast Coat: Series N222 Deco-Tread with 30/50 silica sand — 80–100 SF/gal Second Broadcast Coat: Series N222 Deco-Tread with 30/50 silica sand — 80–100 SF/gal Grout Coat: Series N222 Deco-Tread (pigmented) — 160–200 SF/gal Finish Coat: Series 248 Everthane with 821 Field Colorant — 500–600 SF/gal	Nominal 1/8" system
1/8" Decorative Quartz Epoxy Broadcast — Moderate Duty E1.5 <i>Interior Floor • Moderate Duty • Urethane finish</i>	Lobbies, atriums, reception and waiting areas, public/common spaces, conference or event spaces, dining areas and other decorative moderate-duty floors	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 3 minimum	Cove Base (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Primer: Series N222 Deco-Tread — 250–320 SF/gal First Broadcast Coat: Series N222 Deco-Tread (clear) with decorative quartz — 80–100 SF/gal Second Broadcast Coat: Series N222 Deco-Tread (clear) with decorative quartz — 80–100 SF/gal Grout Coat: Series N222 Deco-Tread (clear) — 160–200 SF/gal Finish Coat: Series 248 Everthane (clear) — 500–600 SF/gal	Nominal 1/8" system
1/16" Decorative Flake Epoxy Broadcast — Light/Moderate Duty E1.6 <i>Interior Floor • Light / Moderate Duty • Urethane finish</i>	Public restrooms, locker room dry areas, stairwells, lobbies, vestibules, reception areas and other decorative light-to-moderate-duty floors	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 3 minimum	Cove Base (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Primer: Series N222 Deco-Tread — 250–320 SF/gal Base Coat: Series N222 Deco-Tread with decorative flake — 160–180 SF/gal Grout Coat 1: Series N222 Deco-Tread (clear) with decorative flake — 160–180 SF/gal Grout Coat 2: Series N222 Deco-Tread (clear) — 160–200 SF/gal Finish Coat: Series 248 Everthane — 500–600 SF/gal	Nominal 1/16" system (includes broadcast flake)
WB1 — WATER-BASED EPOXY SYSTEMS				



Condition	Typical Locations	Surface Preparation	Coat Schedule (Product — Coverage)	Total Build
Clear Sealer WB1.1 <i>Interior Floor • Waterborne Epoxy finish</i>	Same locations as E1.1 where low-odor, water-based application is required — occupied buildings, spaces with limited ventilation, phased renovations	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 2-3 minimum	Primer: Series 288 Enviro-Pox (clear) — 200–250 SF/gal Finish: Series 289 Enviro-Pox (clear) — 200–250 SF/gal Note: Use Series 248 Everthane as a finish coat for added wear resistance	Applied at coverage rate — see coat schedule
Thin Film Solid Color WB1.2 <i>Interior Floor • Waterborne Epoxy finish</i>	Same locations as E1.2 where low-odor, water-based application is required — occupied buildings, spaces with limited ventilation, phased renovations	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 2-3 minimum	Primer: Series 288 Enviro-Pox — 250–320 SF/gal Intermediate: Series 289 Enviro-Pox (pigmented) — 160–200 SF/gal Finish: Series 289 Enviro-Pox (pigmented) — 160–200 SF/gal Note: Use Series 248 Everthane as a finish coat for added wear resistance	Applied at coverage rate — see coat schedule
1/16" Solid Color Epoxy Broadcast — Light Duty WB1.3 <i>Interior Floor • Light Duty • Urethane finish</i>	Offices, administrative areas, low-traffic corridors, break rooms, multipurpose rooms and dry storage areas in occupied buildings or where low-odor application is required	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 2-3 minimum	Cove Base (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Primer: Series 288 Enviro-Pox — 250–320 SF/gal Broadcast Coat: Series 288 Enviro-Pox with 30/50 silica sand — 80–100 SF/gal Grout Coat: Series 288 Enviro-Pox (pigmented) — 160–200 SF/gal Finish Coat: Series 248 Everthane with 821 Field Colorant — 500–600 SF/gal	Nominal 1/16" system
1/8" Solid Color Epoxy Broadcast — Moderate Duty WB1.4 <i>Interior Floor • Moderate Duty • Urethane finish</i>	Corridors, common areas, break and dining areas, equipment rooms, storage and service areas in occupied buildings or where low-odor application is required	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 2-3 minimum	Cove Base (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Primer: Series 288 Enviro-Pox — 250–320 SF/gal First Broadcast Coat: Series 288 Enviro-Pox with 30/50 silica sand — 80–100 SF/gal Second Broadcast Coat: Series 288 Enviro-Pox with 30/50 silica sand — 80–100 SF/gal Grout Coat: Series 288 Enviro-Pox (pigmented) — 160–200 SF/gal Finish Coat: Series 248 Everthane with 821 Field Colorant — 500–600 SF/gal	Nominal 1/8" system



Condition	Typical Locations	Surface Preparation	Coat Schedule (Product — Coverage)	Total Build
1/8" Decorative Quartz Epoxy Broadcast — Moderate Duty WB1.5 <i>Interior Floor • Moderate Duty • Urethane finish</i>	Lobbies, reception and waiting areas, public/common spaces and dining areas in occupied buildings or where a low-odor decorative floor is required	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 2-3 minimum	Cove Base (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Primer: Series 288 Enviro-Pox — 250–320 SF/gal First Broadcast Coat: Series 288 Enviro-Pox (clear) with decorative quartz — 80–100 SF/gal Second Broadcast Coat: Series 288 Enviro-Pox (clear) with decorative quartz — 80–100 SF/gal Grout Coat: Series 288 Enviro-Pox (clear) — 160–200 SF/gal Finish Coat: Series 248 Everthane (clear) — 500–600 SF/gal	Nominal 1/8" system
1/16" Decorative Flake Epoxy Broadcast — Light/Moderate Duty WB1.6 <i>Interior Floor • Light / Moderate Duty • Urethane finish</i>	Public restrooms, locker room dry areas, stairwells, vestibules and reception areas in occupied buildings or where a low-odor decorative floor is required	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 2-3 minimum	Cove Base (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Primer: Series 288 Enviro-Pox — 250–320 SF/gal Base Coat: Series 288 Enviro-Pox with decorative flake — 160–180 SF/gal Grout Coat 1: Series 288 Enviro-Pox (clear) with decorative flake — 160–180 SF/gal Grout Coat 2: Series 288 Enviro-Pox (clear) — 160–200 SF/gal Finish Coat: Series 248 Everthane — 500–600 SF/gal	Nominal 1/16" system (includes broadcast flake)
UC1 — URETHANE CEMENT SYSTEMS				
1/4" Solid Color Urethane Cement — Heavy Duty UC1.1 <i>Interior Floor • Heavy Duty • Urethane finish</i>	Commercial kitchens, food-service and serving areas, mechanical rooms, loading/receiving areas, maintenance shops, laundry rooms, laboratories and heavy-duty service spaces	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 5 minimum	Base / Broadcast Coat: Series N242 Ultra-Tread S with 30/50 aggregate — 37 SF/kit Coving (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Grout Coat: Series N222 Deco-Tread (pigmented) — 160–200 SF/gal Finish Coat: Series 248 Everthane with 821 Field Colorant — 500–600 SF/gal	Nominal 1/4" system



Condition	Typical Locations	Surface Preparation	Coat Schedule (Product — Coverage)	Total Build
1/4" Decorative Quartz Urethane Cement — Heavy Duty UC1.2 <i>Interior Floor • Heavy Duty • Urethane finish</i>	Decorative food-service areas, locker room wet areas, showers, wash areas, laboratories, training or treatment rooms and other heavy-duty wet-service spaces	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 5 minimum	Coving (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Base / Broadcast Coat: Series N242 Ultra-Tread S with decorative quartz — 37 SF/kit Second Broadcast: Series N222 Deco-Tread (clear) with decorative quartz — 80–100 SF/gal Grout Coat: Series N222 Deco-Tread (clear) — 160–200 SF/gal Finish Coat: Series 248 Everthane (clear) — 500–600 SF/gal	Nominal 1/4" system
1/8" Solid Color Urethane Cement — Moderate/Heavy Duty UC1.3 <i>Interior Floor • Moderate / Heavy Duty • Urethane finish</i>	Ground-floor or below-grade slabs with moisture-vapor concerns, mechanical rooms, renovated kitchens or service areas, locker rooms and moderate-to-heavy-duty spaces over existing concrete	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 5 minimum	Coving (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Base / Broadcast Coat: Series N241 Ultra-Tread MVT with aggregate — 90 SF/kit Grout Coat: Series N222 Deco-Tread (pigmented) — 160–200 SF/gal Finish Coat: Series 248 Everthane with 821 Field Colorant — 500–600 SF/gal	Nominal 1/8" system
1/8" Decorative Quartz Urethane Cement — Moderate/Heavy Duty UC1.4 <i>Interior Floor • Moderate / Heavy Duty • Urethane finish</i>	Ground-floor or below-grade slabs with moisture-vapor concerns where a decorative quartz finish is desired, including lobbies, locker rooms, service areas, renovated food-service spaces and other moderate-to-heavy-duty floors	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 5 minimum	Coving (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Base / Broadcast Coat: Series N241 Ultra-Tread MVT with decorative quartz — 90 SF/kit Second Broadcast: Series N222 Deco-Tread (clear) with decorative quartz — 80–100 SF/gal Grout Coat: Series N222 Deco-Tread (clear) — 160–200 SF/gal Finish Coat: Series 248 Everthane (clear) — 500–600 SF/gal	Nominal 1/8" system



Condition	Typical Locations	Surface Preparation	Coat Schedule (Product — Coverage)	Total Build
1/8" Decorative Flake Urethane Cement — Moderate/Heavy Duty UC1.5 <i>Interior Floor • Moderate / Heavy Duty • Urethane finish</i>	Ground-floor or below-grade slabs with moisture-vapor concerns where a decorative flake finish is desired, including restrooms, locker rooms, corridors, vestibules, service areas and other moderate-to-heavy-duty floors	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to ICRI-CSP 5 minimum	Coving (where required): Series N283 , N222 or 288 epoxy with aggregate — Applied at coverage rate Base / Broadcast Coat: Series N241 Ultra-Tread MVT with decorative flake — 90 SF/kit Second Broadcast: Series N222 Deco-Tread (clear) with decorative flake — 80–100 SF/gal Grout Coat: Series N222 Deco-Tread (clear) — 160–200 SF/gal Finish Coat: Series 248 Everthane (clear) — 500–600 SF/gal	Nominal 1/8" system
WP1 — REINFORCED WATERPROOF DECK COATING				
Elevated / Exterior Pedestrian Deck — Heavy Duty WP1.1 <i>Exterior Deck • Heavy Duty • Urethane finish</i>	Elevated plazas, exterior pedestrian walkways, balconies, terraces, rooftop service areas, pedestrian bridges and elevated decks over occupied or unoccupied space below	NACE No. 6/SSPC-SP13, shot-blast or mechanically abrade to the ICRI-CSP profile scheduled	Integral Coving: 4" cove base at vertical interfaces Primer: Series 154 TnemeGuard (thinned) — 4.0–7.0 mils DFT Intermediate: Series 154 TnemeGuard with fiberglass mesh over seams — 10.0–14.0 mils DFT Saturant / Broadcast: Series 154 TnemeGuard with decorative flake — 10.0–14.0 mils DFT Build Coat: Series 154 TnemeGuard — 10.0–14.0 mils DFT Finish Coat: Series 248 Everthane — 500–600 SF/gal	~36.5–52 mils DFT (sum of primer through finish, excluding embedded flake)



WHERE TO GO NEXT

- For CSI 3-part bid/construction specification language built from these same systems, use Section 09 67 23, Resinous Flooring, or contact Atlantic Coating Consultants for a project-specific specification.
- For wall, ceiling, structural steel and exterior envelope coatings, use the companion Architectural Interior & Exterior Short-Form System Reference guide.
- For process-facility applications, use the companion Water Treatment and Wastewater Treatment Short-Form System Reference guides.
- For vehicular traffic decks, secondary containment, immersion-service floors, or specialty exposures not covered here, contact Atlantic Coating Consultants.

Prepared as a service by: Atlantic Coating Consultants | Wally Bates | atlantic@tnemec.com | 484-644-5303